

Description

Solutions for your Environment*

Profile® Wood with Tack is a biodegradable, Hydraulic Mulch (HM) composed of 100% recycled Thermally Refined™ virgin wood fibers and wetting agents (including high-viscosity colloidal polysaccharides). The HM is made in the US, plastic-free, and phytosanitized to eliminate potential weed seeds and pathogens. Upon application, the product forms an intimate bond with the soil surface to create a porous, absorbent and flexible erosion resistant blanket that allows for rapid germination and accelerated plant growth.

Recommended **Applications**

- Erosion control and revegetation for moderate slopes (≤2H:1V)
- Rough graded slopes

Product Composition

Enhancement of vegetation establishment

Technical Data

Physical Properties*	Test Method	Units	Tested Value
Specification for Hydraulically- Applied Wood Fiber Mulch	ASTM D8198-Type1	Compliant	Yes
Mass/Unit Area	ASTM D6566 ¹	g/m² (oz/yd²)	≥ 336 (9.9)
Water Holding Capacity	ASTM D7367	%	≥ 1,200
Material Color	Observed	n/a	Green
Performance Properties*	Test Method	Units	Tested Value
Cover Factor ²	ASTM D8298-Type 1	n/a	≤ 0.25
Percent Effectiveness ³	ASTM D8298-Type 1	%	≥ 75
Vegetation Establishment	ASTM D7322	%	≥ 250
Functional Longevity ⁴	ASTM D5338	months	≤ 3
Environmental Properties*	Test Method	Units	Tested Value
Ecotoxicity ⁵	EPA 2021.0	n/a	Non-Toxic
Biodegradability	ASTM D5338	n/a	Yes
USDA BioPreferred® Biobased Content	ASTM D6866	%	99
Elemental Impurity Limits	ASTM D8082	Pass/Fail	Pass
Carbon Footprint ⁶	Life Cycle Assessment	Unit CO₂e/Unit of product ⁷	≤0.4





Made in USA	
Packaging Data	

When uniformly applied at a rate of 3,000 pounds per acre (3,400 kilograms/hectare) under laboratory conditions. 1 ASTM test methods developed for Rolled Erosion Control Products that have been modified to accommodate Hydraulic Erosion Control Products. 2 Cover Factor is calculated as soil loss ratio of treated surface versus an untreated control surface. 3. % Effectiveness = One minus Cover Factor multiplied by 100%. 4. Functional Longevity is the estimated time period, based upon field observations, that a material can be anticipated to provide erosion control and agronomic benefits as influenced by composition, as well as site-specific conditions, including, but not limited to − temperature, moisture, light conditions, soils, biological activity, vegetative establishment and other environmental factors. 5. 48-hour LC₅₀ > 100% − LC₅₀ refers to the percent concentration of a substance in water when 50% percent mortality of an organism is reached. 50% mortality of the tested species (*Daphnia magna*) could not be achieved when subjected to 100% effluent concentration proving the material to be acutely non-toxic. 6. Cradle to factory gate (Conover, NC) life cycle assessment. 7. *Carbon dioxide equivalent* or CO₂e is a term for describing different greenhouse gases in a common unit. For any quantity and type of greenhouse gas, CO₂e signifies the amount of CO₂ which would have the equivalent global warming impact. The unit of CO₂e per unit of product or 0.4 kg of CO₂e, per kg of product or 0.4 or CO₂e per oz of products. 8. Heated to a temperature greater than 380 degrees Fahrenheit (193 degrees Celsius) for 5 minutes at a pressure greater than 50 psi (345 kPa) in order to be Thermally Refined *M/Processed and to achieve phytosanitation. **Properties Test Method Units Nominal Value Bag Weight** Scale kg (lb) 22.7 (50) Bags per Pallet Observed # 40

UV and weather-resistant plastic bags. Pallets are weather-proof stretch wrapped with UV resistant pallet cover.

Profile Products

750 Lake Cook Road, Ste. 440 Buffalo Grove, IL 60089 800-508-8681 or +1-847-215-3464 www.profileproducts.com

Thermally Processed Wood Fibers⁸ (within a pressurized vessel)

Wetting Agent-Including high-viscosity colloidal polysaccharides

Typical Value

97%